



DATASHEET – PRIMINGFOIL 6298-000-247-91 (UV-LACQUER)

The Likora priming foil is recoatable with all popular lacquer systems

Components:

Basic : Melamine/urearesin-impregnated wood free paper with approx. 25% resin content
Paperweight : 102gsm
Print : Complete water based inks without any contingent of heavy metal
Surface : UV-hardened lacquer with a recoatable surface

End-product:

Final weight : approx. 110gsm
Composition : 45-60% base paper, 20-25% resin content and approx. 10% of lacquer
Tax-number : 48115900

Advices for storage:

Condition : original packaged (unopened)
Premises : dry, 13-22°C, 55-65% humidity
Period of storage : max. 9 months

Characteristics:

Formaldehyde category : E0,5
Light fastness : WS 6 – light blue
Scratch resistance : 500g (Hoffman) or 3,0N (Erichsen)
Tape Pulls : No effect with „3M 810“, or „Scapa 2901“
Surface tension : $\geq 42\text{mN/m}$